



CARACTERISTICAS DE LOS PRINCIPALES P

Producto	Aspecto	Conv.	Comp.		Secado			Espesor micron	Resis. Exter.	Poder Relleno	Elasticidad	Dureza
			1	2	Type	f.p.	s.t.					

ACRILICOS-PUR

ACRY PUR	brillo	AP 10	X	A/H	20'	1-2h	6-8h	40/50	E	E	E	E
PUR 820	brillo	A 22	X	A/H	30'	2h	8h	40/50	E	E	E	E
PUR 821	semibr.	A 21	X	A/H	30'	2h	8h	40/50	E	E	E	E
PUR 825	text.	A 24	X	A/H	30'	2h	8h	100	M	E	E	M
PUR 5050	brillo	A30MS	X	A/H	30'	1h	4-6h	40/50	M	E	E	M
PUR 5038	Brillo	P38	X	A/H	30'	1h	6h	40/50	M	E	E	M
SESTRIDUR	semibr.	AK 52	X	A/H	30'	1h		40/70	E	E	E	E
SESTRIGLOS	Brillo	AK 58	X	A/H	30'	1h		40/70	E	E	E	E

EPOXYS

EPOXIN 2781	brillo	E 80	X	A/H	30'	1-2h	24 h	50	I	E	E	E
EPOXIN 2782	semibr.	E 82	X	A/H	30'	1-2h	24 h	50	I	E	E	E
EPOXIN 2784	Text.	E 84	X	A/H	30'	1-2h	24 h	150	I	E	E	E

EPOXY-PUR

SESTRICOAT	Semibr.	E 85	X	A/H	1 h	1-2h	24 h	75-300	B	E	E	E
------------	---------	------	---	-----	-----	------	------	--------	---	---	---	---

SINTETICOS SECADO RAPIDO

NEORAPID 6800	Brillo	R 13	X	A	20'	50'	4-6h	40/50	M	M	B	M
RAPID LUX 2900	Brillo	R 12	X	A	20'	50'	4-6h	40/50	BB	M	B	M
ESMALTE 6000	Brillo	R 15	X	A	60'	2-3h	18/24	40/50	BB	M	B	M
NEORAPID 6806	Semi b	R 06	X	A	20'	50'	4-6h	40/50	BB	M	B	M
GLICERO 4295	text.	G 42	X	A	20'	50'	4-6h	50	BB	M	B	M
MONOCOUCHE	Semi b	EE 29	X	A	30'	1-2h	24h	70	BB	M	B	M


Secado:

tipo A
type H
f. p.

aire
horno
fuera polvo

REF:

E
B
M excel
bueno
medio



s. t.

seco al tacto

BB bastan

CARACTERISTICAS DE LOS PRINCIPALES P

Producto	Aspecto	Conv.	Comp.		Type	Secado			Espeso r micron	Resis. Exter.	Poder Relleno	Elasticidad	Durez
			1	2		f.p.	s.t.	Duro					

CLOROCAUCHO

CAOUTCH	Semibr.	CL 94	X		A	30'	2-3h	24h	30/40	BB	M	B	M
---------	---------	-------	---	--	---	-----	------	-----	-------	----	---	---	---

SINTETICOS SECADO AL HORNO

GLIC. F 5895	brillo	F 87	X		F	25' a 120°			30-35	B	B	B	E
GLIC. F 5887	semibr.	F 71	X		F	25' a 120°			30-35	B	B	B	E

NITROS

NITROL. 2200	brillo	1340	X		A	5-10'	30'	1h	20-30	BB	I	I	B
JOLLY. 1700	brillo	1545	X		A	5-10'	30'	1-2h	30-40	B	BB	I	B
NITRO MATE	mate	1330	X		A	5-10'	30'	1h	20-30	BB	I	I	B

SINTETICO BROCHA

ALFALUX	brillo	PL 400	X		A	2-3h	4-6h	24h	25-30	E	B	E	M
DELTA LUX	brillo	PL 500	X		A	2-3h	4-6h	24h	25-30	B	B	E	M
ALFAGEL	satn.	PS 250	X		A	1-2h	3-4h	24h	25-30	BB	B	E	M
ZINCOAT TIX	semibr.	PZ 100	X		A	2h	4h	48h	70-80	M	E	E	M

IMPRIMACIONES TINTABLES

EPOXIN PRIM.	semib	E 28	X	A/H	30'			12h	40-50	B	MB	B	B
ANTIOX.MON	mate	L 11	X	A	15'	1h	6-12h		30	B	M	B	B

IMPRIMACIONES STANDARD

EPOXYVIN	semibr	2750	x	A/H	20'	1h	12h		100	E	E	E	E
ETCHPRIMER	semibr	4764	x	A	10'	20'	18- 24h		15-20	B	B	B	B

Secado: tipo A aire REF: E excelle

type H
f. p.
s. t.

horno
fuera polvo
seco al tacto

B **bueno**
M **medio**
BB **bastan**